DNS® premium

Office paper is more than just the paper you use in your office. It communicates your corporate identity, adds a professional edge to your presentations, creates a sense of style with customer invitations, and makes an impact with eye-catching direct mail. It helps you get your job done – better.

Our office paper portfolio offers a wide range of whiteness levels, textures, grammages and recycled papers for all your office applications. Mondi office papers have been specially developed for the different needs of the modern office to achieve optimal results on laser, inkjet and copy machines. We continuously fine tune our office papers for the latest printing technology so you can achieve the best print results, whether in a large corporation or a small home office. See what our office paper portfolio has to offer for your annual reports, presentations, invitations, corporate stationery and general daily correspondence.

Certificates

Further certificates
EU Ecolabel, FSC™, PEFC, ISO 9706 Ageing Resistance, ISO 9001, ISO 14001, ECF, Green Range, ISO 45001, REACH, Free of Heavy Metals, DIN 12281

Technical specification

Parameter Name	Unit	ISO code	60	70	80 [1]	80 [2]	90 [3]	90 [4]	100	120	135	160	200 [5]	200 [6]	250
Basis weight	g/m²	ISO 536	60 ± 2.5	70 ± 2.5	80 ± 3.0	80 ± 3.0	90 ± 3.5	90 ± 3.5	100 ± 4.0	120 ± 4.0	135 ± 4.0	160 ± 6.0	200 ± 6.0	200 ± 6.0	250 ± 6.0
Caliper	µm	ISO 534	85 ± 4	96 ± 3	107 ± 3	108 ± 3	119 ± 3	118 ± 3	131 ± 4	153 ± 4	173 ± 4	202 ± 5	252 ± 6	252 ± 6	315 ± 7
Roughness Bendtsen	ml/min	ISO 8791-2	200 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50	150 ± 50
Opacity	%	ISO 2471	87.0 ± 1	91.0 ± 1	94.0 ± 1	94.0 ± 1	95.0 ± 1	95.0 ± 1	96.0 ± 1	97.5 ± 1	98.0 ± 1	99.0 ± 1	100.0	100.0	100.0
Moisture abs.	%	ISO 287	4.6	4.6/5.2 ± 0.5	5.0 ± 0.5	5.2 ± 0.5	5.0 ± 0.5	5.2 ± 0.5	5.0/5.2 ± 0.5	5.0/5.2 ± 0.5	5.0/5.2 ± 0.5	5.0/5.2 ± 0.5	5.5 ± 0.6	5.2 ± 0.5	5.5 ± 0.6
Brightness UV	%	ISO 2470	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0
CIE Whiteness	%	ISO 11475	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0

Parameter Name	Unit	ISO code	300 [7]	300 [8]	350	400
Basis weight	g/m²	ISO 536	300 ± 8.0	300 ± 8.0	350 ± 11.0	400 ± 12.0
Caliper	µm	ISO 534	378 ± 8	378 ± 8	473 ± 9	548 ± 10
Roughness Bendtsen	ml/min	ISO 8791-2	150 ± 50	150 ± 50	200 ± 50	200 ± 50
Opacity	%	ISO 2471	100.0	100.0	100.0	100.0
Moisture abs.	%	ISO 287	5.5 ± 0.6	5.2 ± 0.5	6.5 ± 0.5	6.5 ± 0.5
Brightness UV	%	ISO 2470	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0	114.0 ± 2.0
CIE Whiteness	%	ISO 11475	170 ± 4.0	170 ± 4.0	170 ± 4.0	170 ± 4.0

[1] A3,A4,Reel | [2] Folio,SRA3 | [3] A3,A4,Reel | [4] Folio,SRA3 | [5] A3,A4,Reel | [6] Folio,SRA3 | [7] A3,A4,Reel | [8] Folio,SRA3 |
Production processes certified according to ISO 9001, ISO 14001 and ISO 45001. Standard measurement uncertainty between laboratories is not incorporated. Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 20494, Requirements for stability for general graphic applications, and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and ISO 45001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA