



Y							
			<b>75</b> g/m²	80 <sub>g/m²</sub>	90 <sub>g/m²</sub>	100g/m²	120 <sub>g/m²</sub>
Whiteness CIE		ISO 11475	169	169	169	169	169
Opacity %		ISO 2471	93	95	96	97	98
Moisture %		ISO 287	5,0	5,0	5,0	5,2	5,2
Bendtsen Roughness	ml/min	ISO 879/2	180	150	150	100	50
Thickness µm		ISO 534	103	108	114	118	125
Bulk µm/g/m²		-	1,37	1,35	1,27	1,18	1,04
Certified		FSC®(1)	<b>V</b>	<b>V</b>	<b>V</b>	<b>V</b>	<b>V</b>
Awarded by		Eco-label <sup>(2)</sup>	<b>V</b>	٧	<b>V</b>	٧	<b>V</b>

MAY 2016

Pre-Print Folio

Technical References - Targets only, without tolerances mentioned Basis weight g/m² - ISO 536

Additional Information about The Navigator Company, Mills and Products: The Navigator Company mills are chain-of-custody certified by NepCon in accordance with FSC-STD-40-004

(NC-COC-001829) and FSC-STD-40-005 (NC CW-001829). In accordance with the requirements of ISO 9706 standard Elemental Chlorine Free (ECF)

Quality Management Systems Standard ISO 9011

Environmental Management Systems Standard SO 14001

Occupational Health and Safety Management Systems Standard OHSAS 18001





