

Technical Data Sheet

Synaps® XM 230

Xerography matt 230 g/m²

version 0.1- 2010-12-03

Property	Test method	Unit	Value
Thickness Average Tolerance	ASTM D-6988	µm µm	200 min.180 / max.220
Weight	ISO 536	g/m ²	230
High temperature limit	Internal Agfa test (0.2% shrinkage)	°C (°F)	>=120 (>= +248)
Low temperature limit	Internal Agfa test (brittleness)	°C (°F)	-40 (-40)
Thermal coefficient of expansion	Internal Agfa test (-40 to 60°C)	µm/mK	tbd
Tear resistance	ASTM D1938	mN	1200
Initial tear strength	ASTM D1004	N	85
Elasticity modulus	ASTM D882	N/mm ²	tbd
Stiffness	ISO 2493	mN	26
Conductivity	DIN IEC 93	Ω/□	1 x 10 ¹¹
BEKK smoothness	ISO 5627	Sec	200
Roughness Ra Rz Rmax	Surftest	µm µm µm	0.7 4.3 5.0
Opacity	ISO 2471	%	92-95
Brightness	ISO 2470C		95-97
Whiteness Cie	ISO 11475		94-96
Gloss 75°	Tappi T480		5
Chemical resistance	Internal Agfa method – 10min	Water NaCl 10% H ₂ SO ₄ 38% Ethanol Aceton	OK OK OK NOK NOK
Mass density	ISO 534	g/cm ³	1.21 ± 0.10
Surface pH			4.9
Surface energy		mN/m	39