



Especificación De Producto

Perfil O 6 mm con pre-corte

	Denominación	Diámetro Interno A (mm)	Espesor B (mm)	Densidad (Kg/m3)
	O 22/6	22± 2	6 (-1,+2)	27 ± 5
	O 28/6	28± 2	6 (-1,+2)	27 ± 5
	O 35/6	35± 2	6 (-1,+2)	27 ± 5
	O 42/6	42± 2	6 (-1,+2)	27 ± 5

Color: Azul

Corte: >75% del espesor

Longitud: 2000mm ± 20mm

Composición Base:

Polietileno de baja densidad (LDPE)
Agente hinchante
Nucleante

Características más importantes:

Espuma de Polietileno expandido de celdilla cerrada fabricado por extrusión directa
No Contiene CFC
Reciclable (grupo 04)
Termoplástico (TP)
Excelente resistencia al agua
Buena resistencia a los disolventes excepto hidrocarburos clorados y alifáticos.

Departamento Emisor: Calidad

Realizado por:

Guerra Yolanda, Calidad

27/07/2010

Revisado por:

Peñarroya Manel, Superv. Calidad
& M. Ambiente

27/07/2010

Aprobado por:

Peñarroya Manel, Superv. Calidad
& M. Ambiente

27/07/2010

Product Specification

Profile O 6 mm with pre-cut

	Denomination	Internal Diameter A (mm)	Thickness B (mm)	Density (Kg/m3)
	O 22/6	22± 2	6 (-1,+2)	27 ± 5
	O 28/6	28± 2	6 (-1,+2)	27 ± 5
	O 35/6	35± 2	6 (-1,+2)	27 ± 5
	O 42/6	42± 2	6 (-1,+2)	27 ± 5

Colour: Blue

Cut: >75% thickness

Length: 2000mm ± 20mm

Composition:

Low Density Polyethylene.
Blowing agent.
Talc.

Main Properties:

PE Foam of closed cells, produced directly by extrusion.
CFC'S free.
Recyclable (code 04)
Thermoplastic (TP)
Excellent resistance to water
Resistance to solvents except chlorinated and aliphatic hydrocarbons

Departamento Emisor: Calidad
Realizado por:

Guerra Yolanda, Calidad

27/07/2010

Revisado por:

Peñarroya Manel, Superv. Calidad
& M. Ambiente

27/07/2010

Aprobado por:

Peñarroya Manel, Superv. Calidad
& M. Ambiente

27/07/2010