



Color Copy - the professional paper guarantees you needle-sharp printouts and brilliant colour reproduction, especially with digital colour laser printing. It is perfectly suitable for documents such as presentations, direct mailings, manuals, corporate plans, business cards and envelopes. Now CO2 neutral!



**Technical Data:** Color Copy

			90	100	120	160
<b>Grammage</b>	g/m <sup>2</sup>	ISO 536	<b>90</b> ± 3.0	<b>100</b> ± 4.0	<b>120</b> ± 4.5	<b>160</b> ± 6.0
<b>Caliper</b>	mm/1000	ISO 534	<b>98</b> ± 4	<b>106</b> ± 4	<b>126</b> ± 4	<b>166</b> ± 6
<b>Stiffness L&amp;W</b>	MD mN	ISO 2493	<b>130</b> ± 30	<b>160</b> ± 30	<b>245</b> ± 30	<b>490</b> ± 40
<b>Stiffness L&amp;W</b>	CD mN	ISO 2493	<b>70</b> ± 15	<b>90</b> ± 25	<b>130</b> ± 25	<b>250</b> ± 30
<b>Smoothness Bekk</b>	sec	ISO 5627	<b>105</b> ± 25	<b>105</b> ± 25	<b>105</b> ± 25	<b>105</b> ± 25
<b>Opacity</b>	%	ISO 2471	<b>min 92.0</b>	<b>min 93.0</b>	<b>min 95.0</b>	<b>min 97.0</b>
<b>Brightness with UV</b>	D65 %	ISO 2470	<b>110.0</b> ± 1.5	<b>110.0</b> ± 1.5	<b>110.0</b> ± 1.5	<b>110.0</b> ± 1.5
<b>CIE Whiteness</b>		ISO 11475	<b>161</b> ± 3.0	<b>161</b> ± 3.0	<b>161</b> ± 3.0	<b>161</b> ± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA



Color Copy - the leading paper guarantees you needle-sharp printouts and brilliant colour reproduction, especially with digital colour laser printing. It is perfectly suitable for documents such as presentations, direct mailings, manuals, corporate plans, business cards and envelopes. Now CO2 neutral!



**Technical Data:** Color Copy

			200	220	250	280	300	350
<b>Grammage</b>	g/m <sup>2</sup>	ISO 536	200 ± 6.0	220 ± 6.0	250 ± 7.0	280 ± 8.0	300 ± 8.0	350 ± 8.0
<b>Caliper</b>	mm/1000	ISO 534	200 ± 7	220 ± 7	245 ± 8	275 ± 9	305 ± 9	350 ± 10
<b>Stiffness L&amp;W</b>	MD mN	ISO 2493	min 620	min 800	min 900	min 1300	min 1600	min 2000
<b>Stiffness L&amp;W</b>	CD mN	ISO 2493	min 330	min 400	min 500	min 700	min 800	min 1000
<b>Smoothness Bekk</b>	sec	ISO 5627	120 ± 30	120 ± 30	120 ± 30	110 ± 30	70 ± 30	70 ± 30
<b>Opacity</b>	%	ISO 2471	min 98.0	min 99.0	min 99.0	min 99.0	min 99.0	min 99.0
<b>Brightness with UV</b>	D65 %	ISO 2470	110.0 ± 1.5	110.0 ± 1.5	110.0 ± 1.5	110.0 ± 1.5	110.0 ± 1.5	110.0 ± 1.5
<b>CIE Whiteness</b>		ISO 11475	161 ± 3.0	161 ± 3.0	161 ± 3.0	161 ± 3.0	161 ± 3.0	161 ± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA