

Oppboga Supreme™ - preliminary

Solid bleached board, double coated on both sides

SUB- STANCE	THICKNESS		BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
	g/m ²	μm pt	MD	CD	MD	CD
400	410		550	275	27	14
450	520		825	400	40	19
500	600		1175	600	57	29
600	720		1950	1000	94	48



White. Smooth. Vibrant

APPLICATIONS

Luxury packaging • high-end graphics

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

Embossing • foil and film lamination •
varnishing • die cutting • creasing •
perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)±4%
Thickness (DIN ISO 534)±4%
Bending stiffness (ISO 5629)-15%
ISO Brightness C/2° (ISO 2470) min. 92
Smoothness (ISO 8791-4) max 1.4μm

Printing Surface Properties

ISO Brightness95
CIE Whiteness D65/10° (ISO 11475) 135
Surface smoothness (PPS) 0.9μm
Gloss 75° (ISO 8254-1)48%