

Silvana Natural Recycled

<i>Specification</i>	<i>Unit</i>	<i>Norm</i>	<i>Value</i>	<i>Tolerances</i>
Gramaje <i>Substance</i> Grammage	g/m^2	ISO 536	80, 90, 100, 120, 135, 150, 170, 190, 250, 300, 350	+/- 4 %
Espesor Caliper Épaisseur	μm	ISO 534	80 gr. 100 90 gr. 113 100 gr. 125 120 gr. 150 135 gr. 169 150 gr. 180 170 gr. 204 190 gr. 228 250 gr. 300 300 gr. 345 350 gr. 403	+/- 5 %
Lisura Bekk Smoothness Bekk Lissé Bekk	s	UNE 57093	80 a 120 gr. 30 135 a 170 gr. 25 190 a 250 gr. 20 300 a 350 gr. 15	+/- 7 +/- 6 +/- 5 +/- 5
Humedad absoluta Absolute moisture Humidité absolute	%	ISO 287	80 a 100 gr. 6 120 a 350 gr. 7	+/- 1
Blancura Whiteness Blancheur	CIE	ISO 2470	80	+/- 3
Opacidad Opacity Opacité	%	ISO 2471	80 gr. 95 90 gr. 97 100 gr. 98 120 gr. 99 135 gr. 99 150 gr. 99 170 gr. 99 190 gr. 99 250 gr. 99 300 gr. 99 350 gr. 99	+/- 1

Los datos citados son indicativos.

La estructura y los valores de la información de los productos pueden ser modificados.

